

ADSS Fiber Optic Cable 100 SPAN B1.3 PE

ADSS Fiber Optic Cable 100 SPAN B1.3 PE

Variants

12 Core 24 Core 48 Core 96 Core

Details

ADSS Optical Fiber Cable

Fiber Specifications

Parameter	Specification
Material	Quartz Glass (Silicon Dioxide)
Core	9 μ m (High Refractive Index)
Cladding	125 μ m (Low Refractive Index)
Coating	245 μ m (Protective Resin)

Optical Parameters

Parameter	Requirement	Standard
Core Non-Circularity	$\leq 6\%$	ITU-T G.652
Cladding Diameter	$125.0 \pm 0.7 \mu\text{m}$	-
Core / Cladding Concentricity	$\leq 0.6 \mu\text{m}$	-
Cladding Non-Circularity	$\leq 1.0\%$	-
Coating Diameter	$245 \pm 10 \mu\text{m}$	-

Cladding / Coating Concentricity	? 12 ?m	-
Attenuation Coefficient	1310 nm: ? 0.35 dB/km 1550 nm: ? 0.21 dB/km	-
Zero Dispersion Slope	? 0.092 ps/(nm ² ·km)	-
Zero Dispersion Wavelength	1300 – 1324 nm	-
Polarization Dispersion	? 0.20 ps/?km	-
Mode Field Diameter (1310 nm)	9.0 ± 0.4 ?m	-
Cut-off Wavelength	1170 – 1330 nm	-
Chromatic Dispersion	1288 – 1339 nm: ? 3.4 ps/(nm·km) 1550 nm: ? 18 ps/(nm·km) 1625 nm: ? 22 ps/(nm·km)	-

Cable Parameters

Parameter	Value
Fibers per Loose Tube	6
Number of Tubes	2
Inner Sheath Thickness	1.0 mm
Outer Sheath Thickness	1.7 mm
Aramid Area	2.8 mm ²
Cable Diameter	13 mm (±5%)
Cable Cross-Section	106 mm ²
Cable Weight	105 kg/km (±10%)

Mechanical & Environmental Performance

Parameter	Value
RTS (Rated Tensile Strength)	4800 N
MAT (Maximum Allowable Tension)	1900 N
Static Bending Radius	? 174 mm
Dynamic Bending Radius	? 290 mm
Operating Temperature	-40°C to +70°C
Installation Temperature	-10°C to +40°C

Test Requirements

Test Type	Standard	Key Criteria
Tensile Test	IEC 60794-1-21-E1	RTS: No break at 100% RTS. UOS (60% RTS): Fiber strain 0.35%, no added attenuation. MAT (40% RTS): Strain 0.05%.
Crush Test	IEC 60794-1-21-E3	? 0.1 dB attenuation at 1550 nm under 2200 N; no residual attenuation.
Impact Test	IEC 60794-1-21-E4	450 g weight, 1 m height, 5 impacts. No sheath cracks or residual attenuation.
Repeated Bending	IEC 60794-1-21-E6	30 bends under 150 N load. No cracks or residual attenuation.
Torsion Test	IEC 60794-1-21-E7	±180° twist, 10 cycles. No added attenuation or sheath damage.

Temperature Cycling	IEC 60794-1-22-F1	-40°C to +65°C, 2 cycles. Attenuation 0.05 dB/km at 1550 nm.
Water Penetration	IEC 60794-1-22-F7	1 m head for 1 hour. No leakage.