

Optical Fiber Cable 12 core FRP

Optical Fiber Cable 12 core FRP

Variants

6MM (Drum) 6.2MM (Coil) 8MM (Coil) GYFXY 6.2mm CH

Details

12 Core Optical Fiber Cable

Fiber Color Code

Fiber Color Code			
1	Blue	7	Red
2	Orange	8	Black
3	Green	9	Yellow
4	Brown	10	Violet
5	Gray	11	Pink
6	White	12	Aqua

Loose Tube & Filler Rod Color Code

Color Code for Loose Tube (LT) & Filler Rod (FR)		
12 Core	Element	LT

Cable Structure & Parameters

Cable Structure & Parameters			
Optical Fiber	Core	—	12
Loose Tube	Material	—	PBT
	Diameter	mm	1.9
Strength Member	Material #1	—	FRP
	Diameter	mm	0.8
	Material #2	—	2400D Yarn
Sheath	Material	—	MDPE
	Diameter	mm (±0.3)	6.2
Mechanical	Tension	N	400 / 1000
	Crush	N/100mm	300 / 1000

Fiber Properties (ITU-T G.652D)

Fiber Properties (ITU-T G.652D)	
Fiber Type	Single mode
Fiber Material	Doped silica
Attenuation Coefficient	@1310nm ? 0.36 dB/km, @1383nm ? 0.32 dB/km, @1550nm ? 0.22 dB/km, @1625nm ? 0.30 dB/km
Point Discontinuity	? 0.05 dB
Cable Cut-off Wavelength	? 1260 nm
Zero-dispersion Wavelength	1300 ~ 1324 nm
Zero-dispersion Slope	? 0.093 ps/(nm ² ·km)

Chromatic Dispersion	@1288~1339nm ? 3.5 ps/(nm·km), @1271~1360nm ? 5.3 ps/(nm·km), @1550nm ? 18 ps/(nm·km), @1625nm ? 22 ps/(nm·km)
PMDQ (Quadrature Average)	? 0.2 ps/km ^{1/2}
Mode Field Diameter @1310nm	9.2 ± 0.4 μm
Core / Clad Concentricity Error	? 0.5 μm
Cladding Diameter	125.0 ± 0.7 μm
Cladding Non-circularity	? 1.0%
Primary Coating Diameter	245 ± 10 μm
Proof Test Level	100 kpsi (=0.69 GPa), 1%
Temperature Dependence (0°C to +70°C)	? 0.1 dB/km @1310nm & 1550nm

Optical Cable Characteristics

Mechanical & Environmental Characteristics	
Cable Bending Radius	10 × cable diameter (during operation), 20 × cable diameter (during installation)
Operating Temperature Range	-40°C to +60°C
Storage / Transport Temperature Range	-50°C to +70°C
Installation Temperature Range	-20°C to +50°C

Packing & Marking

Packing

Drum Type / Coil Type	Wooden drum suitable for long distance shipment / Coil type easy for shipment
Protection	Covered by plastic buffer sheet and sealed by strong wooden battens
Testing Reserve	At least 1 m of inside cable end reserved for testing
Standard Drum / Coil Length	2000m \pm 5%
Permitted Single Length	Not less than 90% of standard length per drum, for quantity not exceeding 10% of total supply
Total Quantity	At least the ordered quantity